

## TIG RODS

## Mild Steel

LNT 25 .....	358
LNT 26 .....	359

## Low Alloy Steel

LNT 28 .....	360
LNT Ni1 .....	361
LNT NiMo1 .....	362
LNT Ni2.5 .....	363
LNT 12 .....	364
LNT 19 .....	365
LNT 20 .....	366
LNT 502 .....	367
LNT 9Cr(P91) .....	368

## Stainless Steel

LNT 304LSi .....	369
LNT 304L .....	370
LNT 347Si .....	371
LNT 316LSi .....	372
LNT 316L .....	373
LNT 318Si .....	374
LNT 4439Mn .....	375
LNT 4500 .....	376
LNT 4462 .....	377
LNT Zeron® 100X .....	378
LNT 309LHF .....	379
LNT 309LSi .....	380
LNT 309L .....	381
LNT 304H .....	382
LNT 310 .....	383

## Nickel alloys

LNT NiCro 60/20 .....	384
LNT NiCro 70/19 .....	385
LNT NiCroMo 59/23 .....	386
LNT NiCu 70/30 .....	387
LNT NiTi .....	388

## Copper alloys

LNT CuNi30 .....	389
LNT CuSn6 .....	390
LNT CuSi3 .....	391

## Aluminium alloys

SuperGlaze® TIG 1070 .....	392
SuperGlaze® TIG 1100 .....	393
SuperGlaze® TIG 4043 .....	394
SuperGlaze® TIG 4047 .....	395
SuperGlaze® TIG 5183 .....	396
SuperGlaze® TIG 5183 .....	397
SuperGlaze® TIG 5356 .....	398
SuperGlaze® TIG 5554 .....	399
SuperGlaze® TIG 5754 .....	400

## Autogenous Wires

LNG I .....	401
LNG II .....	402
LNG IV .....	403

TRAINING TIPS &amp; TRICKS

# TIG WELDING ALUMINIUM



# LNT 25

## CLASSIFICATION

<b>AWS A5.18</b>	ER70S-3	<b>A-Nr</b>	1	<b>Mat-Nr</b>	1.5112
<b>EN ISO 636-A</b>	W 42.5 W25i	<b>F-Nr</b>	6		
		<b>9606 FM</b>	1		

## GENERAL DESCRIPTION

Solid rod for welding general construction in mild steel  
High impact values

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## APPROVALS

<b>TÜV</b>	<b>CE</b>
+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

<b>C</b>	<b>Mn</b>	<b>Si</b>
0.08	1.1	0.6

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J)	
						-20°C	-50°C
Typical values	I1	AW	450	560	26	170	100

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
<b>General structural steels</b>	EN 10025	S185, S235, S275, S355
<b>Ship plates</b>	ASTM A131	Grade A, B, D, AH32 to DH 36.
<b>Cast steels</b>	EN 10213-2	GP240R
<b>Pipe material</b>	EN 10208-1	L210, L240, L290, L360
	EN 10208-2	L240NB, L290NB, L360NB, L360QB, L240MB, L290MB, L360MB, L415MB, L415NB
	API 5LX	X42, X46, X52, X60
	EN 10216-1	P235T1, P235T2, P275T1
	EN 10217-1	P275T2, P355N
<b>Boiler &amp; pressure vessel steels</b>	EN 10028-2	P235GH, P265GH, P295GH, P355GH
<b>Fine grained steels</b>	EN 10025 part 3	S275, S355, S420
	EN 10025 part 4	S275M, S275ML, S355M, S355ML, S420M, S420ML

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	Note : Cut length = 1000 mm
5 kg PE-Tube	X	X	X	X	

LNT 25: rev. C-EN25-01/02/16

# LNT 26

## CLASSIFICATION

<b>AWS A5.18</b>	ER70S-6	<b>A-Nr</b>	1	<b>Mat-Nr</b>	1.5125
<b>EN ISO 636-A</b>	W 42.5 W35i1	<b>F-Nr</b>	6		
		<b>9606 FM</b>	1		

## GENERAL DESCRIPTION

Solid rod for welding general construction in mild steel  
Smooth bead appearance

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## APPROVALS

<b>TÜV</b>	<b>CE</b>
+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

<b>C</b>	<b>Mn</b>	<b>Si</b>
0.1	1.5	0.9

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J)		
						-20°C	-30°C	-50°C
<b>Typical values</b>	I1	AW	460	580	26	170	170	120

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
<b>General structural steels</b>	EN 10025	S185, S235, S275, S355
<b>Ship plates</b>	ASTM A131	Grade A, B, D, AH32 to DH 36.
<b>Cast steels</b>	EN 10213-2	GP240R
<b>Pipe material</b>	EN 10208-1	L210, L240, L290, L360
	EN 10208-2	L240NB, L290NB, L360NB, L360QB, L240MB, L290MB, L360MB, L415MB, L415NB
	API 5LX	X42, X46, X52, X60
	EN 10216-1	P235T1, P235T2, P275T1
	EN 10217-1	P275T2, P355N
<b>Boiler &amp; pressure vessel steels</b>	EN 10028-2	P235GH, P265GH, P295GH, P355GH
<b>Fine grained steels</b>	EN 10025 part 3	S275, S355, S420
	EN 10025 part 4	S275M, S275ML, S355M, S355ML, S420M, S420ML

## PACKAGING AND AVAILABLE SIZES

Diameter [mm]	1.6	2.0	2.4	3.2	Note : Cut length = 1000 mm
<b>5 kg PE-Tube</b>	X	X	X	X	

LNT 26: rev. C-EN25-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT 28

## CLASSIFICATION

AWS A5.28	ER80S-G	A-Nr	10
		F-Nr	6
		9606 FM	2

## GENERAL DESCRIPTION

Solid rod for welding of weather resisting steels  
Excellent mechanical properties

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## APPROVALS

CE

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Ni	Cu
0.1	1.4	0.75	0.8	0.3

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) -20°C
Typical values	I1	AW	570	620	26	80

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
Weather resisting steels	EN 10155	S 235 J 0 W
		S 235 J 2 W
		S 355 J 0 W
		S 355 J 2 W
		S 355 K 2 G 1 W

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.4	Note : Cut length = 1000 mm
5 kg PE-Tube	X	

LNT 28: rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT Ni1

## CLASSIFICATION

AWS A5.28	ER80S-Ni1	A-Nr	12
EN ISO 636-A	W 42 6 W3Ni1	F-Nr	6
		9606 FM	1

## GENERAL DESCRIPTION

Solid rod for welding fine grained and low alloy nickel steels  
 High impact value at low temperature [-60°C]  
 Typical offshore applications

## SHIELDING GASES (ACC. ISO 14175)

II Inert gas Ar (100%)

## APPROVALS

GL	TÜV	CE	DNV
+	+	+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Ni
0.1	1.2	0.6	0.9

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength	Tensile strength	Elongation	Impact ISO-V(J)
			[N/mm <sup>2</sup> ]	[N/mm <sup>2</sup> ]	[%]	-60°C
Typical values	II	AW	480	580	30	60

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
General structural steels	EN 10025	S275, S355
Ship plates	ASTM A131	Grade A, B, D, E, AH32 to EH36
Cast steels	EN 10213-2	GP240R
Pipe material	EN 10208-1	L290 GA, L360GA
EN 10208-2	L290, L360, L415	
API 5LX	X42, X46, X52, X60, X65	
EN 10216-1	P275T1	
EN 10217-1	P275 T2, P355 N	
Fine grained steels	EN 10025 part 3	S275, S355, S420, S460
EN 10025 part 4	S275, S355, S420, S460	
EN 10028	P355NL-1, P460NL-1	

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.0	Note : Cut length = 1000 mm
5 kg PE-Tube	X	X	X	X	

LNT Ni1: rev. C-EN28-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
 Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
 THE WELDING EXPERTS®

# LNT NiMo1

## CLASSIFICATION

AWS A5.28	ER1005-G	A-Nr	2
ISO 16834-A	W Mn3Ni1Mo	F-Nr	-
		9606 FM	2

## GENERAL DESCRIPTION

Alloy TIG rod suitable for welding high tensile strength steels  
Excellent mechanical properties

## SHIELDING GASES (ACC. ISO 14175)

II Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Ni	Mo	Ti
0.08	1.7	0.7	0.9	0.35	0.17

GTAW

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)
Typical values	II	AW	760	800	18

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
Pipe material	EN 10208-2	L480, L550
API 5LX	X65, X70, X80	
Fine grained steels	EN 10025 part 6	S460, S500, S550, S620

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.4
5 kg PE-Tube	X	X

LNT NiMo1 : rev. C-EN03-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT Ni2.5

## CLASSIFICATION

AWS A5.28	ER80S-Ni2	A-Nr	10
EN ISO 636-A	W2 Ni2	F-Nr	6
		9606 FM	1

## GENERAL DESCRIPTION

Solid rod for welding fine grained and low alloy nickel steels  
 High impact value at low temperature [-60°C as welded and -90°C after stress relieving 15h/580°C].  
 Typical offshore applications

## SHIELDING GASES (ACC. ISO 14175)

II Inert gas Ar (100%)

## APPROVALS

TÜV	CE
+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Ni
0.1	1.1	0.55	2.4

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J)	
						-62°C	-90°C
Typical values	II	AW	525	605	28	280	133

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
General structural steels	EN 10025	S355
Pipe material	EN 10208-2	L360, L415, L445
API 5 LX	X52, X56, X60, X65	
Fine grained steels	EN 10025 part 3	S355, S420, S460
EN 10025 part 4	S355, S420, S460	
Low temperature steels	EN 10028-4	11 MnNi 5-3, 13 MnNi 6-3, 15 NiMn 6
	(12 Ni 14 G 1, G 2)	
EN 10222-3	13 MnNi 6-3, 15 NiMn 6	

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.4	3.0	
5 kg PE-Tube	X	X	Note : Cut length = 1000 mm

LNT Ni2.5: rev. C-EN26-01/02/16

# LNT 12

## CLASSIFICATION

AWS A5.28	ER70S-A1	A-Nr	2	Mat-Nr	1.5424
ISO 21952-A	W MoSi	F-Nr	6		
		9606 FM	1/3		

## GENERAL DESCRIPTION

Solid rod for welding creep resistant 0.5%Mo steels and Fine grained steels for low temperature applications in the as welded condition with service temperatures in range -20°C to +500°C

## SHIELDING GASES (ACC. ISO 14175)

II Inert gas Ar (100%)

## APPROVALS

TÜV	DNV	GL	DB
+	+	+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Mo
0.1	1.2	0.6	0.5

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J)	
						+20°C	-20°C
Typical values	II	AW	635	670	22	170	110

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
<b>Elevated temperature steel</b>	EN 10028-2	P295 G H, P355 G H, 16 Mo 2
EN 10222-2	17 Mo 3, 14 Mo 6	
<b>Fine grained steels</b>	EN 10025 part 3	S275, S355, S420
EN 10025 part 4	S275, S355, S420	

## APPLICATION ADVICE

Preheating welding joint acc.EN 1011-1  
Stress relieving 580-650°C if necessary

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.0	<i>Note: Cut length = 1000 mm</i>
5 kg PE-Tube	X	X	X	X	

LNT 12: rev. C-EN25-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.



# LNT 19

## CLASSIFICATION

AWS A5.28	ER80S-B2*	A-Nr	3	Mat-Nr	1.7339
ISO 21952-A	W CrMo1Si	F-Nr	6		
* Nearest classification		9606 FM	3		

## GENERAL DESCRIPTION

Solid rod for welding creep and hydrogen resistant Cr-Mo steels (1,25Cr - 0,5Mo)  
Service temperature up to 550°C

## SHIELDING GASES (ACC. ISO 14175)

11 Inert gas Ar (100%)

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Mo
0.1	1.0	0.6	1.2	0.5

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]	Impact ISO-V(J) +20°C
Typical values	11	PWHT 700°C/1h	540	640	22	250

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
Elevated temperature steel	EN 10028-2	13 CrMo4-5
EN 10083-1	25 CrMo 4	
EN 10222-2	14 CrMo 4-5	
Tool steel	DIN 17210	16 MnCr 5

## PACKAGING AND AVAILABLE SIZES

Diameter [mm]	2.0	2.4	3.0	
5 kg PE-Tube	X	X	X	Note : Cut length = 1000 mm

LNT 19: rev. C-EN26-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# LNT 20

## CLASSIFICATION

<b>AWS A5.28</b>	ER90S-B3*	<b>A-Nr</b>	4	<b>Mat-Nr</b>	1.7384
<b>ISO 21952-A</b>	W CrMo2Si	<b>F-Nr</b>	6		
* Nearest classification		<b>9606 FM</b>	4		

## GENERAL DESCRIPTION

Solid rod for welding creep and hydrogen resistant Cr-Mo steels [2,25Cr - 1Mo]

Service temperature up to 600°C

## SHIELDING GASES (ACC. ISO 14175)

It Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Mo
0.08	1.0	0.6	2.5	1.0

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) +20°C
Typical values	It	PWHT 700°C/1h	560	640	22	140

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
Creep and hydrogen resistant steels	EN 10028-2	10CrMo 9-10
EN 10222-2	12CrMo 9-10	

## APPLICATION ADVICE

Preheating welding joint acc. EN 1011-1, 200-250°C

Post weld heat treatment at 690-740°C

## PACKAGING AND AVAILABLE SIZES

Diameter [mm]	2.0	2.4	
5 kg PE-Tube	X	X	<i>Note : Cut length = 1000 mm</i>

LNT20: rev. C-EN26-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT 502

## CLASSIFICATION

<b>AWS A5.28</b>	ER80S-B6	<b>A-Nr</b>	4	<b>Mat-Nr</b>	1.7373
<b>ISO 21952-A</b>	W CrMo5Si*	<b>F-Nr</b>	6		
* Nearest classification		<b>9606 FM</b>	4		

## GENERAL DESCRIPTION

Solid rod for welding of creep and hydrogen resistant 5%Cr, 0.5%Mo steels  
Service temperature up to 550°C

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Mo
0.09	0.6	0.3	5.7	0.6

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) +20°C
Typical values	I1	PWHT 750°C/1h	560	650	20	80

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
<b>Creep and hydrogen resistant steels</b>	SEW 028	12CrMo 19-5 and corresponding steels
ASTM A182	F5	
ASTM A213	T5	
ASTM A335	P5	
ASTM A336	F5	
ASTM A369	FP5	
ASTM A387	Grade 5	

## APPLICATION ADVICE

Recommended preheat and interpass temperature 200-300°C  
Recommended post weld heat treatment at range 675-750°C (time depending on material thickness)

## PACKAGING AND AVAILABLE SIZES

<b>Diameter (mm)</b>	2.4	<i>Note : Cut length = 1000 mm</i>
<b>5 kg PE-Tube</b>	X	

LNT 502 rev. C-EN26-01/02/16

# LNT 9Cr(P91)

## CLASSIFICATION

AWS A5.28	ER90S-B39	A-Nr	5
ISO 21952-A	W CrMo91	F-Nr	6
		9606 FM	4

## GENERAL DESCRIPTION

Solid rod for welding of creep and hydrogen resistant 9% Cr, 1% Mo steels  
Service temperature up to 650°C

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Mo	Ni	Nb	V	Cu
0.11	0.8	0.25	8.9	1.0	0.5	0.06	0.2	0.06

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) -20°C
Typical values	I1	SR 750°C/3h	500	700	18	70

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type	Standard	Type
Creep and hydrogen resistant steels	EN 10222-2	X10CrMo V9-1 steels		
	ASTM	A199 Grade T91	ASME	SA 182-F91
		A200 Grade T91		
		A213 Grade T91		SA 213-T91
		A335 Grade P91		SA 335-P91
		A336 Grade F91		SA 336-F91
				SA 369-FP91
				SA 387-Grade 91
			SA 387-Grade 91	

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.4	
5 kg PE-Tube	X	X	Note : Cut length = 1000 mm

LNT 9Cr(P91); rev. C-EN26-12/05/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT 304LSi

## CLASSIFICATION

<b>AWS A5.9</b>	ER308LSi	<b>A-Nr</b>	8	<b>Mat-Nr</b>	1.4316
<b>ISO 14343-A</b>	W 19 9 L Si	<b>F-Nr</b>	6		
		<b>9606 FM</b>	5		

## GENERAL DESCRIPTION

Solid rod with extra low carbon for welding austenitic CrNi-steels  
With increased silicon for improved wettability

## SHIELDING GASES (ACC. ISO 14175)

II Inert gas Ar (100%)

## APPROVALS

<b>DNV</b>	<b>TÜV</b>	<b>CE</b>	<b>DB</b>
+	+	+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

<b>C</b>	<b>Mn</b>	<b>Si</b>	<b>Cr</b>	<b>Ni</b>	<b>Mo</b>
0.02	2.0	0.8	20	10	0.1

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V[J]	
						+20°C	-196°C
Typical values	II	AW	467	622	37	147	67

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088 -1/-2	EN 10213-4	Mat. Nr	ASTM/ACI A240/A312/A351	UNS
<b>Extra low carbon [C &lt; 0.03%]</b>					
	X2CrNi19-11		1.4306	(TP)304 L	S30403
				CF-3	J92500
	X2CrNi18-10		1.4311	(TP)304LN	S30453
				302, 304	S30400
<b>Medium carbon [C &gt; 0.03%]</b>					
	X4CrNi18-10		1.4301	(TP)304	S30409
		G-X5CrNi19-10	1.4308	CF-8	J92600
<b>Ti-,Nb stabilized</b>					
	X6CrNiTi18-10		1.4541	(TP)321	S32100
				(TP)321H	S32109
	X6 CrNiNb18-10		1.4550	(TP)347	S34700
		G-X5CrNiNb19-10	1.4552	CF-8C	J92710

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.0	1.2	1.6	2.0	2.4	3.2	Note : Cut length = 1000 mm
5 kg PE-Tube	X	X	X	X	X	X	

LNT 304LSi rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# LNT 304L

## CLASSIFICATION

AWS A5.9	ER308L	A-Nr	8	Mat-Nr	1.4316
ISO 14343-A	W 19 9 L	F-Nr	6		
		9606 FM	5		

## GENERAL DESCRIPTION

Solid rod with extra low carbon for welding austenitic CrNi-steels  
High resistance to intergranular corrosion and oxidizing environments

## SHIELDING GASES (ACC. ISO 14175)

l1 Inert gas Ar (100%)

## APPROVALS

CE

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.01	1.7	0.4	20	10	0.1

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Typical values	Shielding gas	Condition	0.2% proof strength	Tensile strength	Elongation	Impact ISO-V(J)	
			[N/mm <sup>2</sup> ]	[N/mm <sup>2</sup> ]	[%]	+20°C	-196°C
	l1	AW	472	692	34	120	91

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	EN 10213-4	Mat. Nr	ASTM/ACI A240/A312/A351	UNS
<b>Extra low carbon [C &lt; 0.03%]</b>					
	X2CrNi19-11		1.4306	(TP)304 L	S30403
	X2CrNi18-10		1.4311	CF-3 (TP)304LN 302, 304	J92500 S30453 S30400
<b>Medium carbon [C &gt; 0.03%]</b>					
	X4CrNi18-10	G-X5CrNi19-10	1.4301 1.4308	(TP)304 CF-8	S30409 J92600
<b>Ti-,Nb stabilized</b>					
	X6CrNiTi18-10		1.4541	(TP)321 (TP)321H	S32100 S32109
	X6CrNiNb18-10	G-X5CrNiNb19-10	1.4550 1.4552	(TP)347 CF-8C	S34700 J92710

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.2	1.6	2.0	2.4	3.2	Note : Cut length = 1000 mm
5 kg PE-Tube	X	X	X	X	X	

LNT 304L: rev. C-EN24-01/02/16

# LNT 347Si

## CLASSIFICATION

<b>AWS A5.9</b>	ER347Si	<b>A-Nr</b>	8	<b>Mat-Nr</b>	1.4551
<b>ISO 14343-A</b>	W 19 9 NbSi	<b>F-Nr</b>	6		
		<b>9606 FM</b>	5		

## GENERAL DESCRIPTION

Solid rod for welding Ti or Nb stabilized stainless CrNi-steels  
High resistance to intergranular corrosion and oxidizing environments

## SHIELDING GASES (ACC. ISO 14175)

It Inert gas Ar (100%)

## APPROVALS

<b>TÜV</b>	<b>CE</b>	<b>DB</b>
+	+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

<b>C</b>	<b>Mn</b>	<b>Si</b>	<b>Cr</b>	<b>Ni</b>	<b>Mo</b>	<b>Nb</b>
0.05	1.4	0.7	19.5	9.5	0.01	0.6

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength	Tensile strength	Elongation	Impact ISO-V(J)	
			[N/mm <sup>2</sup> ]	[N/mm <sup>2</sup> ]	[%]	+20°C	-196°C
Typical values	It	AW	400	650	35	80	45

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	EN 10213-4	Mat. Nr	ASTM/ACI A240/A312/A351	UNS
<b>Ti-,Nb stabilized</b>					
	X6CrNiTi18-10		1.4541	(TP)321 (TP)321H	S32100 S32109
	X6CrNiNb18-10		1.4550	(TP)347 (TP)347h	S34700 S34709
		G-X5CrNiNb19-10	1.4552	CF-8C	J92710
<b>Non stabilized</b>					
	X4CrNi18-10		1.4301	302 (TP)304	S30400
	X2CrNi19-11		1.4306	(TP)304L	S30403
		G-X5CrNi19-10	1.4308 1.4312	CF-8 (TP)304H	J92600 S30409

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	Note : Cut length = 1000 mm
5 kg PE-Tube	X	X	X	X	

LNT 347Si : rev. C-EN24-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT 316LSi

## CLASSIFICATION

AWS A5.9	ER316LSi	A-Nr	8	Mat-Nr	1.4430
ISO 14343-A	W 19 12 3 LSi	F-Nr	6		
		9606 FM	5		

## GENERAL DESCRIPTION

Solid rod with extra low carbon for welding stainless CrNiMo-steels  
See also LNT 316L, high silicon for improved wettability

## SHIELDING GASES (ACC. ISO 14175)

It Inert gas Ar (100%)

## APPROVALS

DNV	TÜV	DB	CE	ABS
+	+	+	+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.03	1.9	0.8	18.5	12.0	2.7

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]	Impact ISO-V(J)	
						+20°C	-196°C
Typical values	It	AW	484	624	32	100	82

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	EN 10213-4	Mat. Nr	ASTM/ACI A240/A312/A351	UNS
<b>Extra low carbon [C &lt; 0.03%]</b>					
	X2CrNiMo1712-2		1.4404	(TP)316L	S31603
	X2CrNiMo18-14-3		1.4435	CF-3M	J92800
	X2CrNiMoN17-11-2		1.4406	(TP)316L	S31603
	X2CrNiMoN17-13-3		1.4429	(TP)316LN	S31653
<b>Medium carbon [C &gt; 0.03%]</b>					
	X4CrNiMo17-12-2		1.4401	(TP)316	S31600
	X4CrNiMo17-13-3		1.4436		
		G-X5CrNiMo19-11	1.4408	CF 8M	J92900
<b>Ti-,Nb stabilized</b>					
	X6CrNiMoTi17-12-2		1.4571	316 Ti	S31635
	X6CrNiMoNb17-12-2		1.4580	316 Cb	S31640
	X6CrNiNb18-10		1.4550	(TP)347	S34700
		G-X5CrNiNb19-10	1.4552	CF-8C	J92710

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.0	1.2	1.6	2.0	2.4	3.2	Note : Cut length = 1000 mm
5 kg PE-Tube	X	X	X	X	X	X	

LNT 316LSi: rev. C-EN24-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.



# LNT 316L

## CLASSIFICATION

AWS A5.9	ER316L	A-Nr	8	Mat-Nr	1.4430
ISO 14343-A	W 19 12 3 L	F-Nr	6		
		9606 FM	5		

## GENERAL DESCRIPTION

Solid rod with extra low carbon for welding austenitic CrNiMo-steels  
High resistance to intergranular corrosion and general corrosion conditions

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.01	1.5	0.5	18.5	12	2.7

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Typical values	Shielding gas	Condition	0.2% proof	Tensile strength	Elongation	Impact ISO-V(J)		
			strength (N/mm <sup>2</sup> )	(N/mm <sup>2</sup> )	(%)	+20°C	-120°C	-196°C
	I1	AW	400	620	35	100	80	40

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	EN 10213-4	Mat. Nr	ASTM/ACI A240/A312/A351	UNS
<b>Extra low carbon [C &lt; 0.03%]</b>					
	X2CrNiMo17-12-2		1.4404	(TP)316L	S31603
	X2CrNiMo18-14-3		1.4435	CF-3M	J92800
	X2CrNiMoN17-11-2		1.4406	(TP)316LN	S31653
	X2CrNiMoN17-13-3		1.4429		
<b>Medium carbon [C &gt; 0.03%]</b>					
	X4CrNiMo17-12-2		1.4401	(TP)316	S31600
	X4CrNiMo17-13-3		1.4436		
		G-X5CrNiMo19-11	1.4408	CF 8M	J92900
<b>Ti-,Nb stabilized</b>					
	X6CrNiMoTi17-12-2		1.4571	316 Ti	S31635
	X6CrNiMoNb17-12-2		1.4580	316Cb	S31640
	X6CrNiNb18-10		1.4550	(TP)347	S34700
		G-X5CrNiNb19-10	1.4552	CF-8C	J92710

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2
5 kg PE-Tube	X	X	X	X

LNT 316L: rev. C-EN25-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

GTAW

# LNT 318Si

## CLASSIFICATION

AWS A5.9	ER318*	A-Nr	8	Mat-Nr	1.4576
ISO 14343-A	W 19 12 3 NbSi	F-Nr	6		
* Nearest classification		9606 FM	5		

## GENERAL DESCRIPTION

Solid rod for welding Ti or Nb stabilized stainless CrNiMo-steels  
High resistance to intergranular corrosion and general corrosion conditions

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo	Nb
0.05	1.4	0.7	18.7	11.7	2.5	0.7

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Typical values	Shielding gas	Condition	0.2% proof strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]	Impact ISO-V(J)	
						+20°C	-196°C
	I1	AW	420	680	35	70	45

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	EN 10213-4	Mat. Nr	ASTM/ACI A240/A312/A351	UNS
<b>Extra low carbon [C &lt; 0.03%]</b>					
	X2CrNiMo17-12-2		1.4404	(TP)316L	S31603
	X2CrNiMo18-14-3		1.4435	CF-3M	J92800
	X2CrNiMoN17-11-2		1.4406	(TP)316L	S31603
	X2CrNiMoN17-13-3		1.4429	(TP)316LN	S31653
<b>Medium carbon [C &gt; 0.03%]</b>					
	X4CrNiMo17-12-2		1.4401	(TP)316	S31600
	X4CrNiMo17-13-3		1.4436		
		G-X5CrNiMo19-11	1.4408	CF 8M	J92900
<b>Ti-,Nb stabilized</b>					
	X6CrNiMoTi17-12-2		1.4571	316 Ti	S31635
	X6CrNiMoNb17-12-2		1.4580	316 Cb	S31640
	X6CrNiNb18-10		1.4550	(TP)347	S34700
		G-X5CrNiNb19-10	1.4552	CF-8C	J92710

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2
5 kg PE-Tube	X	X	X	X

LNT 318Si rev. C-EN24-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT 4439Mn

## CLASSIFICATION

ISO 14343-A	W 18 16 5 N L*	A-Nr	9*	Mat-Nr	1.4453
		F-Nr	-		
	* Nearest classification	9606 FM	5		

## GENERAL DESCRIPTION

Solid rod for welding AISI 317L, 317LN or equivalent stainless steels  
 For welding 316L if increased molybdenum content is important  
 High resistance to pitting, intergranular and stress corrosion  
 Fully austenitic weld metal

## SHIELDING GASES (ACC. ISO 14175)

II Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo	N
0.02	7	0.4	18	16	4.5	0.15

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]	Impact ISO-V(J) -196°C
Typical values	II	AW	440	650	35	80

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	EN 10213-4	Mat. Nr	ASTM/ACI	UNS
<b>Fully austenitic CrNiMo corrosion resistant steels</b>					
	X2CrNiMoN17-11-2		1.4406	[TP]316LN	S31653
	X2CrNiMoN17-13-3		1.4429	[TP]316LN	S31653
	X2CrNiMo18-14-3		1.4435	[TP]316L	S31603
	X2CrNiMo18-15-4		1.4438	317L	S31725
	X2CrNiMoN17-13-5		1.4439	317LN	S31726
	G-X2CrNiMoN17-13-4	G-X2CrNiMo17-13-4	1.4446		
	G-X6CrNiMo17-13	G-X6CrNiMo17-13	1.4448		

## PACKAGING AND AVAILABLE SIZES

Diameter [mm]	2.0	2.4
5 kg PE-Tube	X	X

LNT 4439Mn, rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
 THE WELDING EXPERTS®

GTAW

# LNT 4500

## CLASSIFICATION

AWS A5.9	ER385	A-Nr	9
ISO 14343-A	W 20 25 5 Cu L	F-Nr	6
		9606 FM	5

## GENERAL DESCRIPTION

Solid rod for welding of fully austenitic steels of type 20%Cr / 25%Ni / 4.5%Mo / 1.5%Cu  
Highly corrosion resistant in sulphuric and phosphoric acid

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo	Cu
0.01	1.7	0.4	20	25	4.5	1.5

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) -196°C
Typical values	I1	AW	380	560	35	80

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	EN 10213-4	Mat. Nr
Fully austenitic NiCrMoCu and CrNiMoCu steels			
	X5NiCrMoCuTi20-18	G-X7NiCrMoCuNb25-20	1.4500
		G-X2NiCrMoCuN20-18	1.4506
		G-X2NiCrMoCuN25-20	1.4531
	X1NiCrMoCuN25-20-5	G-X2NiCrMoCuN25-20	1.4536
			1.4539
		G-X7CrNiMoCuNb18-18	1.4585
	X5NiCrMoCuNb22-18		1.4586

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.4
5 kg PE-Tube	X	X

LNT 4500: rev. C-EN24-01/02/16

# LNT 4462

## CLASSIFICATION

AWS A5.9	ER2209	A-Nr	8	Mat-Nr	1.4462
ISO 14343-A	W 22 9 3 N L	F-Nr	6		
		9606 FM	5		

## GENERAL DESCRIPTION

Solid rod for welding duplex stainless steels  
High resistance to general corrosion, pitting and stress corrosion conditions

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo	N
0.01	1.6	0.5	22.5	8.5	3.0	0.15

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) -60°C
Typical values	I1	AW	675	829	27	200

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	Mat. Nr	UNS
<b>Duplex stainless steels</b>			
	X2CrNiMoN22-5-3	1.4462	S31803
		1.4417	S31500
	X2CrNiN23-4	1.4362	S32304
	X3CrNiMoN27-5-2	1.4460	S31200
	X2CrNiMoN21-5-1	1.4162	S32101

Dissimilar joints such as un- and low alloy steel to duplex stainless steel

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	Note : Cut length = 1000 mm
5 kg PE-Tube	X	X	X	X	

LNT 4462: rev. C-EN24-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# LNT Zeron® 100X

## CLASSIFICATION

<b>AWS A5.9</b>	ER2594	<b>A-Nr</b>	8
<b>ISO 14343-A</b>	W 25 9 4 N L	<b>F-Nr</b>	6
		<b>9606 FM</b>	5

## GENERAL DESCRIPTION

Solid rod for welding Zeron® 100 and other super duplex stainless steel grades  
High resistance to pitting and crevice corrosion in seawater

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo	Cu	W	N
0.02	0.6	0.23	25	9.3	3.6	0.6	0.6	0.22

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) -50°C
Typical values	I1	AW	655	934	42	100

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	Mat. Nr	UNS		
<b>Regular and super duplex stainless steels</b>					
	X2CrNiMoN25-7-4		1.4410		
	X4CrNiMoN27-5-2		1.4460		
	X2CrNiMoN22-5-3		1.4462	2205	S31803
		GX6 CrNiMo 24-8-2	1.4463		
				CD-4MCu	S32550
				Zeron® 100	S32760

Super duplex stainless Steel grades: chemical composition approximately:  
24-27% Cr, 6-9% Ni, 3-4% Mo, 0.10-0.25% N alloyed also with Cu and/or W

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	Note : Cut length = 1000 mm
5 kg PE-Tube	X	X	X	X	

LNT Zeron® 100X: rev. C-EN25-01/02/16

# LNT 309LHF

## CLASSIFICATION

AWS A5.9	ER309L	A-Nr	8	Mat-Nr	1.4332
ISO 14343-A	W 23 12 L	F-Nr	6		
		9606 FM	5		

## GENERAL DESCRIPTION

Solid rod for welding stainless steel to carbon steel  
 Low susceptibility to embrittlement  
 Minimum 18FN ferrite in weldmetal

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.02	2.0	0.35	24	13	0.1

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength(N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J)	
						+20°C	+40°C
Typical values	I1	AW	488	608	33	167	171

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	Mat. Nr	ASTM/ACI A240/A312/A351	UNS
<b>Corrosion resistant cladsteels</b>				
	X2CrNiN18-10	1.4311	(TP)304LN	S30453
	X2CrNi19-11	1.4306	(TP)304L	S30403
			CF-3	J92500
	X4CrNi18-10	1.4301	(TP)304	S30400

Dissimilar metals (mild and low alloy steel to stainless steel)  
 Build-up welding on mild and low alloy steel

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0
5 kg PE-Tube	X	X

LNT 309LHF Rev. C-EN25-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
 Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
 THE WELDING EXPERTS®

# LNT 309LSi

## CLASSIFICATION

AWS A5.9	ER309LSi	A-Nr	8	Mat-Nr	1.4332
ISO 14343-A	W 23 12 LSi	F-Nr	6		
		9606 FM	5		

## GENERAL DESCRIPTION

Solid rod for welding stainless steel to carbon steel  
With high silicon for improved wettability

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## APPROVALS

TÜV	CE
+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.02	2.0	0.8	23.5	13	0.1

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) -120°C
Typical values	I1	AW	400	600	35	65

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	Mat. Nr	ASTM/ACI	UNS
<b>Corrosion resistant cladsteels</b>				
	X2CrNiN18-10	1.4311	(TP)304LN	S30453
	X2CrNi19-11	1.4306	(TP)304L	S30403
			CF-3	J92500
	X4CrNi18-10	1.4301	(TP)304	S30400

Dissimilar metals (mild and low alloy steel to stainless steel)

Build-up welding on mild and low alloy steel

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	
5 kg PE-Tube	X	X	X	X	<i>Note : Cut length = 1000 mm</i>

LNT 309LSi rev. C-EN24-01/02/16



# LNT 309L

## CLASSIFICATION

<b>AWS A5.9</b>	ER309L	<b>A-Nr</b>	8	<b>Mat-Nr</b>	1.4332
<b>ISO 14343-A</b>	W 23 12 L	<b>F-Nr</b>	6		
		<b>9606 FM</b>	5		

## GENERAL DESCRIPTION

Solid rod for welding stainless steel to carbon steel

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## APPROVALS

CE

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.01	1.65	0.5	24	13	0.1

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)
Typical values	I1	AW	390	600	35

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	Mat. Nr	ASTM/ACI	UNS
<b>Corrosion resistant cladsteels</b>				
	X2CrNiN18-10	1.4311	(TP)304LN	S30453
	X2CrNi19-11	1.4306	(TP)304L	S30403
		CF-3	J92500	
	X4CrNi18-10	1.4301	(TP)304	S30400

Dissimilar metals (mild and low alloy steel to stainless steel)

Build-up welding on mild and low alloy steel

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4
<b>5 kg PE-Tube</b>	X	X	X

LNT 309L: rev. C-EN04-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# LNT 304H

## CLASSIFICATION

AWS A5.9	ER308H	A-Nr	8	Mat-Nr	1.4948
ISO 14343-A	W 19 9 H	F-Nr	6		
		9606 FM	5		

## GENERAL DESCRIPTION

Solid rod for welding austenitic CrNi-steels  
Especially for high temperature applications (up to 730°C)  
Low sensitivity to precipitation of intermetallic phases

## SHIELDING GASES (ACC. ISO 14175)

11 Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.07	1.9	0.4	20	9.2	0.1

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation [%]	Impact ISO-V(J) +20°C
Typical values	11	AW	370	600	35	80

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	EN 10213-4	Mat. Nr	ASTM/AISI	UNS
Medium carbon (C > 0.03%)	X4CrNi18-10		1.4301	(TP)304 (TP)304H	302 S30400 S30409
		G-X5CrNi19-10	1.4308 1.4948	CF 8	J92600

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.4
5 kg PE-Tube	X	X

LNT 304H rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT 310

## CLASSIFICATION

AWS A5.9	ER310	A-Nr	9	Mat-Nr	1.4812
ISO 14343-A	W 25 20	F-Nr	6		
		9606 FM	5		

## GENERAL DESCRIPTION

Solid rod for welding heat resistant Cr- and CrNi-steels (25%Cr-20%Ni)  
High resistance to oxidation and scaling up to approx. 1100°C

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.1	1.7	0.5	26	21	0.1

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]	Impact ISO-V(J) +20°C
Typical values	I1	AW	360	600	35	100

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	EN 10213-4	Mat. Nr	ASTM/ACI	UNS
	X10CrAl24		1.4762		
		G-X25CrNiSi18-9	1.4825		
		G-X40CrNiSi22-9	1.4826		
	X15CrNiSi20-12		1.4828		
		G-X25CrNiSi20-14	1.4832		
	X15CrNiSi25-20		1.4841	3105	S31008
				CK20	J94202
	X12CrNi25-21		1.4845		
		G-X40CrNiSi25-20	1.4848	HK40	

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4
5 kg PE-Tube	X	X	X

LNT 310 : rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# LNT NiCr 60/20

## CLASSIFICATION

AWS A5.14	ERNiCrMo-3	A-Nr	-	Mat-Nr	2.4831
ISO 18274	S Ni 6625 (NiCr22Mo9Nb)	F-Nr	43		
		9606 FM	6		

## GENERAL DESCRIPTION

Solid rod for welding of nickel alloys  
 Extreme resistance to various corrosion forms  
 High chromium and molybdenum content

## SHIELDING GASES (ACC. ISO 14175)

I1	Inert gas Ar (100%)
I3	Inert gas Ar+ 0.5-95% He

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Ni	Cr	Mo	Nb	Fe
0.03	0.1	0.1	bal.	22	9	3.5	0.4

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof	Tensile strength	Elongation	Impact ISO-V(J)	
			strength (N/mm <sup>2</sup> )	(N/mm <sup>2</sup> )	(%)	+20°C	-196°C
Typical values	I1	AW	520	800	35	130	100

## EXAMPLES OF MATERIALS TO BE WELDED

Ni-alloy grades	DIN/EN	Mat. Nr	ASTM/ACI	UNS
<b>NiCrMo-steel Type alloy 625 and welding dissimilar high NiCrMo-steels for corrosion and heat resisting purposes</b>				
	X1NiCrMoCuN25-20-6	1.4529	Alloy 925	N08925
	X1NiCrMoCu25-20-5	1.4539	Alloy 904L	N08904
	X1CrNiMoCuN20-18-7	1.4547	Alloy 254	S31254
	X2NiCrAlTi32-20	1.4558	Alloy 800L	N08800
	G-X10NiCrNb32-20	1.4859		
	X10NiCrAlTi32-20	1.4876	Alloy 800/800H	N08800/-10
	NiCr22Mo6Cu	2.4618	Alloy G	N06007
	NiCr22Mo7Cu	2.4619	Alloy G-3	N06985
	NiCr21Mo6Cu	2.4641	Alloy 825hMo	N08821
	NiCr20CuMo	2.4660	Alloy 20	N08020
	NiCr15Fe	2.4816	B168-Alloy 600	N06600
	NiCr22Mo9Nb	2.4856	B443-Alloy 625	N06625
	NiCr21Mo	2.4858	B424-Alloy 825	N08825
	NiCr20Ti	2.4951	Alloy 75	N06075
	NiCr20TiAl	2.4952	Alloy 80A	N07080
<b>Low alloy steels</b>				
	10Ni14 (3.5% Ni)	1.5637	ASTM A333 Grade 3	-
	12Ni19, X12Ni5	1.5680	-	K41583
<b>9% Ni-steel for LNG storage tanks</b>				
	X8Ni9	1.5662	A353/A353M	-
	X8Ni9 / 8%Ni	1.5662	A553/A553M Type I/II	- / K71340

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	Note : Cut length = 1000 mm
2.5 kg PE-Tube	X	X	X	X	

LNT NiCr 60/20; rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
 Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT NiCro 70/19

## CLASSIFICATION

AWS A5.14	ERNiCr-3	A-Nr	-	Mat-Nr	2.4806
ISO 18274	S Ni 6082 (NiCr20Mn3Nb)	F-Nr	43		
		9606 FM	6		

## GENERAL DESCRIPTION

Solid rod for welding nickel based alloys, dissimilar metals and cladding  
High resistance to oxidation and high impact toughness at low temperature

## SHIELDING GASES (ACC. ISO 14175)

I1	Inert gas Ar (100%)
I3	Inert gas Ar+ 0.5-95% He

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Ni	Cr	Nb	Cu	Fe
0.03	3.0	0.2	bal.	20	2.5	0.1	1.0

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Typical values	Shielding gas	Condition	0.2% proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J)	
						+20°C	-196°C
	I1	AW	400	680	40	150	120

## EXAMPLES OF MATERIALS TO BE WELDED

Ni-alloy grades	BS3076	DIN 17744/17465	Mat. Nr	ASTM/ACI	UNS
		SEW 595		B366	
<b>Ni-base high Cr alloyed steel for low and high corrosion searching application</b>					
	Na 14	NiCr15Fe	2.4816	B168-Alloy 600	N06600
		LC-NiCr15Fe	2.4817	Alloy 600L	N06600
		NiCr20Ti	2.4951	Alloy 75	
		NiCr20TiA1	2.4952	Alloy 80A	N07080
	Na 15	X10NiCrAlTi32-20	1.4876	Alloy 800/800H	N0800/10
		NiCr23Fe	2.4851	Alloy 601(H)	N06601
	Na 17	X12NiCrSi36-16	1.4864	330	N08330
		G-X40NiCrNb35-25	1.4852		
		G-X40NiCrSi35-25	1.4857	HP	

Un- and low alloy heat and creep resistant steel to stainless steel

## APPLICATION ADVICE

Limit heat-input (HI<1.5kJ/mm) and interpass temperature (Ti<150°C)

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.4	3.2	
2.5 kg PE-Tube	X	X	X	Note : Cut length = 1000 mm

LNT NiCro 70/19: rev. C-EN24-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# LNT NiCrMo 59/23

## CLASSIFICATION

AWS A5.14	ERNiCrMo-13	A-Nr	-	Mat-Nr	2.4607
ISO 18274	S Ni 6059 (NiCr23Mo16)	F-Nr	43		
		9606 FM	6		

## GENERAL DESCRIPTION

Solid rod for welding nickel base alloys with high CrMo content  
 Excellent resistance against pitting, stress, and crevice corrosion in acid sulfur phosphorus and chlorine surroundings  
 Suitable for dissimilar joints

## SHIELDING GASES (ACC. ISO 14175)

I1 Inert gas Ar (100%)

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Ni	Cr	Mo	Al	Fe
0.015	0.5	0.06	59	23	16	0.4	1.5

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) +20°C
Typical values	I1	AW	400	700	25	90

## EXAMPLES OF MATERIALS TO BE WELDED

Ni-alloy grades	DIN 17744	Mat. Nr	ASTM / ACI	UNS
<b>Ni-base high CrMo steel</b>				
	NiCr23Mo16	2.4605		N06059
	NiMo16Cr16Ti	2.4610	C-4	N06455
	NiMo16Cr15Ti	2.4819	C-276	N10276
	NiCr21Mo14W	2.4602	C-22	N06022
	NiCr22Mo9Nb	2.4856	625	N06625
<b>High Mo stainless steel for high corrosion environments</b>				
	EN 10088-1/-2			
	X1NiCrMoCuN25-20-7	1.4529	904hMo	N08925
	X1CrNiMoCuN20-18-7	1.4547		S31254

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	
2.5 kg PE-Tube	X	X	X	Note : Cut length = 1000 mm

LNT NiCrMo 59/23: rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT NiCu 70/30

## CLASSIFICATION

AWS A5.14	ERNiCu-7	A-Nr	-	Mat-Nr	2.4377
ISO 18274	S Ni 4060 (NiCu30MnTi)	F-Nr	42		
		9606 FM	6		

## GENERAL DESCRIPTION

Solid rod for welding Monel and NiCu-alloys to mild and low alloy steels  
 Can be used as well for welding mild and low alloy steels to NiCu alloys  
 High resistance to seawater corrosion

## SHIELDING GASES (ACC. ISO 14175)

I1	Inert gas Ar (100%)
I3	Inert gas Ar+ 0.5-95% He

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Ni	Cu	Fe	Ti
0.06	3.5	0.5	65	30	1.1	2.0

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J)	
						+20°C	-196°C
Typical values	I1	AW	350	560	40	160	140

## EXAMPLES OF MATERIALS TO BE WELDED

Ni-alloy grades	BS3076	DIN 17743	Mat. Nr	ASTM/ACI	UNS
	NA 13	NiCu30Fe	2.4360	Monel 400	N04400
		G-NiCu30Nb	2.4365		
	NA 18	NiCu30Al	2.4375	Monel K500	N05500

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	
2.5 kg PE-Tube	X	X	X	X	<i>Note : Cut length = 1000 mm</i>

LNT NiCu 70/30: rev. C-EN26-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
 Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
 THE WELDING EXPERTS®

# LNT NiTi

## CLASSIFICATION

AWS A5.14	ERNi1	A-Nr	-	Mat-Nr	2.4155
ISO 18274	S Ni 2061 (NiTi3)	F-Nr	41		
		9606 FM	6		

## GENERAL DESCRIPTION

Solid wire for welding pure nickel and nickel alloys and joining these materials with non alloy/low alloy steel  
Suitable for surfacing carbon steels

## SHIELDING GASES (ACC. ISO 14175)

I1	Inert gas Ar (100%)
I3	Inert gas Ar+ 0.5-95% He

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Ni	Ti	Fe
0.03	0.5	0.4	bal.	2.8	0.06

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) +20°C
Typical values	I1	AW	250	460	30	120

## EXAMPLES OF MATERIALS TO BE WELDED

DIN-classification	Mat. Nr	ASTM/ACI
Ni 99.6	2.4060	
Ni 99.8	2.4050	
Ni 99.6Si	2.4056	
Ni 99.4Fe	2.4062	
Ni 99.2	2.4066	Alloy 200
LC-Ni 99	2.4068	Alloy 201
LC-Ni 99.6	2.4061	Alloy 205
NiMn10	2.4108	
NiMn5	2.4116	

## PACKAGING AND AVAILABLE SIZES

Diameter [mm]	2.0	2.4	
2.5 kg PE-Tube	X	X	<i>Note : Cut length = 1000 mm</i>

LNT NiTi: rev. C-EN24-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
Fumes: Safety Data Sheets (SDS) are available on our website.



# LNT CuNi30

## CLASSIFICATION

<b>AWS A5.7</b>	ERCuNi	<b>A-Nr</b>	-	<b>Mat-Nr</b>	2.0837
<b>EN 14640</b>	S Cu 7158 (CuNi30)	<b>F-Nr</b>	34		
		<b>9606 FM</b>	-		

## GENERAL DESCRIPTION

Solid rod for welding copper-nickel alloys containing 10-30%Ni

## SHIELDING GASES (ACC. ISO 14175)

I1	Inert gas Ar (100%)
I3	Inert gas Ar+ 0.5-95% He

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Ni	Si	Ti	Fe
bal.	0.75	30	0.05	0.35	0.5

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Hardness HB	Impact ISO-V(I) +20°C
<b>Typical values</b>	I1	AW	250	400	30	70	100

## EXAMPLES OF MATERIALS TO BE WELDED

Cu-alloy grades	Standard	Type	Mat. Nr	UNS
<b>Copper-nickel wrought alloys</b>				
	DIN 17664	CuNi10Fe1Mn	2.0872	C 70600
		CuNi30Mn1Fe	2.0882	C 71500
		CuNi30Fe2Mn2	2.0883	C 71600
<b>Copper-nickel cast alloys</b>				
	DIN 17658	G-CuNi10	2.0815	
		G-CuNi30	2.0835	

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4
<b>2.5 kg PE-Tube</b>	X	X	X

LNT CuNi30 rev. C-EN24-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# LNT CuSn6

## CLASSIFICATION

<b>AWS A5.7</b>	ERCuSn-A	<b>A-Nr</b>	-	<b>Mat-Nr</b>	2.1022
<b>EN ISO 24373</b>	S Cu 5180 (CuSn6P)	<b>F-Nr</b>	33		
		<b>9606 FM</b>	-		

## GENERAL DESCRIPTION

Solid rod for welding of copper-tin alloys

## SHIELDING GASES (ACC. ISO 14175)

I1	Inert gas Ar (100%)
I3	Inert gas Ar+ 0.5-95% He

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Sn	P
bal.	6.0	0.2

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2 proof strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Hardness HB	Impact ISO-V(J) +20°C
Typical values	I3	AW	150	260	20	75	80

## EXAMPLES OF MATERIALS TO BE WELDED

Cu-alloy grades	Standard	Type	Mat. Nr
<b>Copper-tin wrought alloys</b>			
	DIN 17662	CuSn4	2.1016
		CuSn6	2.1020
		CuSn8	2.1030
<b>Copper-tin cast alloys</b>			
	DIN 1705	G-CuSn2ZnPb	2.1098
		G-CuSn5ZnPb	2.1096
		G-CuSn6ZnNi	2.1093

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.4	3.2
2.5 kg PE-Tube	X	X	X

LNT CuSn6: rev. EN 27-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# LNT CuSi3

## CLASSIFICATION

<b>AWS A5.7</b>	ERCuSi-A	<b>A-Nr</b>	-	<b>Mat-Nr</b>	2.1461
<b>EN ISO 24373</b>	S Cu 6560 (CuSi3Mn)	<b>F-Nr</b>	32		
		<b>9606 FM</b>	-		

## GENERAL DESCRIPTION

Solid rod for GTA-welding of low alloy copper grades  
High temperature and corrosion resistant

## SHIELDING GASES (ACC. ISO 14175)

I1	Inert gas Ar (100%)
I3	Inert gas Ar+ 0.5-95% He

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Sn	Mn	Si	Zn
bal.	0.1	1.0	3.0	0.1

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Hardness HB	Impact ISO-V(J) +20°C
Typical values	I1	AW	120	350	40	95	60

## EXAMPLES OF MATERIALS TO BE WELDED

Copper, low alloy copper and copper-zinc alloys

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.4
2.5 kg PE-Tube	X	X

LNT CuSi3 rev. C-EN24-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.  
Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# SuperGlaze® TIG 1070

## CLASSIFICATION

ISO 18273	S Al 1070 (Al99.7)	A-Nr	-
		F-Nr	21
		Mat-Nr	3.0259

## GENERAL DESCRIPTION

Highly resistant to chemical corrosion and good crack resistance

Suitable for electrical and chemical applications utilizing aluminium base metal with little or no alloying elements

Like all 1xxx filler alloys, Al 1070 is one of the softest aluminium MIG wire and requires extra care to ensure good feeding

## SHIELDING GASES (ACC. ISO 14175)

It	Inert gas Ar (100%)
Flow rate	14.2 - 23.6L/min

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	V	Ti	Be
min. 99.7	max. 0.2	max. 0.25	max. 0.04	max. 0.03	max. 0.03	0	max. 0.04	max. 0.05	max. 0.03	max. 0.0003

Notes : Unspecified elements should not exceed a total of 0.03%

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]
Typical values	It	AW	20-30	65-80	29-35

## PHYSICAL PROPERTIES

Melting range	: 647 - 658°C
Density	: approximately 2700 kg/m <sup>3</sup>

## APPLICATIONS

Joining 1xxx alloys to themselves or other alloys  
Bus Bars  
Electrical Boxes

Heat Exchangers  
Metallizing  
Electro-technical, Chemical, Construction and Food Industry

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.4	3.2	Note : Cut length = 1000 mm
5 kg cardboard box	X	X	X	

Superglaze® TIG 1070: rev. C-EN02-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# SuperGlaze® TIG 1100

## CLASSIFICATION

<b>AWS 5.10</b>	R1100	<b>A-Nr</b>	-
<b>ISO 18273</b>	S Al 1100 (Al99.0Cu)	<b>F-Nr</b>	21
<b>EN 573.3</b>	EN AW-Al99.0Cu	<b>Mat-Nr</b>	-

## GENERAL DESCRIPTION

Highly resistant to chemical corrosion and good crack resistance

Suitable for electrical and chemical applications utilizing aluminium base metal with little or no alloying elements

Like all 1xxx filler alloys, Al 1100 is one of the softest aluminium MIG wire and requires extra care to ensure good feeding

## SHIELDING GASES (ACC. ISO 14175)

<b>It</b>	Inert gas Ar (100%)
<b>Flow rate</b>	14.2 - 23.6L/min

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Be
min. 99.0	A	A	0.05-0.20	max. 0.05	0	0	max. 0.10	0	max. 0.0003

Notes : A = Si+Fe max. 0.95

Notes : Unspecified elements should not exceed a total of 0.15%

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]
<b>Typical values</b>	It	AW	20-30	65-80	29-35

## PHYSICAL PROPERTIES

<b>Melting range</b>	: 647 - 658°C
<b>Density</b>	: approximately 2700 kg/m <sup>3</sup>

## APPLICATIONS

Joining 1xxx alloys to themselves or other alloys  
Bus Bars  
Electrical Boxes

Heat Exchangers  
Metallizing  
Electro-technical, Chemical, Construction and Food Industry

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	4.0	Note : Cut length = 1000 mm
<b>5 kg cardboard box</b>	X	X	X	X	X	

SuperGlaze® TIG 1100 rev. C-EN01-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# SuperGlaze® TIG 4043

## CLASSIFICATION

AWS 5.10	R4043	A-Nr	-
ISO 18273	S Al 4043A (AlSi5)	F-Nr	23
EN 573.3	EN AW-AISI5	Mat-Nr	3.2245

## GENERAL DESCRIPTION

Designed for welding heat treatable base alloys and more specifically 6xxx Series Alloys

Lower melting point and fluidity than 5xxx series filler alloys

Low sensitivity to weld cracking with 6xxx base alloys

Suitable for sustained elevated temperature service. i.e. above 650C

## SHIELDING GASES (ACC. ISO 14175)

I1	Inert gas Ar (100%)
Flow Rate	: 14.2 - 23.6 L/min

## APPROVALS

ABS	DB	TÜV
+	+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Be
bal.	4.5-6.0	max. 0.6	0.05-0.020	max. 0.05	0	-	max. 0.1	0	max. 0.0003

Notes : Unspecified elements should not exceed a total of 0.15%

## MECHANICAL PROPERTIES. TYPICAL. ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)
Typical values	I1	AW	20-40	120-165	3-18

## PHYSICAL PROPERTIES

Melting range	: 573 - 625°C
Density	: approximately 2680 kg/m3

## APPLICATIONS

For welding 6XXX alloys, and most casting alloys  
Automotive components such as frame and drive shafts  
Bicycle frames

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	4.0	4.8	Note : Cut length = 1000 mm
5 kg cardboard box	X	X	X	X	X	X	

Superglaze® TIG 4043: rev. C-EN22-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# SuperGlaze® TIG 4047

## CLASSIFICATION

<b>AWS 5.10</b>	R4047	<b>A-Nr</b>	-
<b>ISO 18273</b>	S Al 4047 (AlSi12)	<b>F-Nr</b>	23
<b>EN 573.3</b>	EN AW-AlSi12	<b>Mat-Nr</b>	3.2585

## GENERAL DESCRIPTION

Lower melting point and higher fluidity than 4043 wires

Can be used as a substitute for 4043 to increase silicon content in the weld metal and minimize hot cracking and produce higher fillet weld shear strength

Can be used as a brazing alloy

## SHIELDING GASES (ACC. ISO 14175)

It	Inert gas Ar (100%)
Flow Rate	: 14.2 - 23.6 L/min

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Be
bal.	11-13	max. 0.8	max. 0.30	max. 0.15	0.10	0	max. 0.20	0	max. 0.0003

Notes : Unspecified elements should not exceed a total of 0.15%

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)
Typical values	It	AW	60-80	130-190	5-20

## PHYSICAL PROPERTIES

Melting range	: 573 - 585°C
Density	: approximately 2680 kg/m <sup>3</sup>

## APPLICATIONS

For welding 6XXX alloys, and most casting alloys  
Automotive components, radiators and air conditioning

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.4	3.2	4.0	Note : Cut length = 1000 mm
5 kg cardboard box	X	X	X	X	

Superglaze® TIG 4047: rev. C-EN22-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# SuperGlaze® TIG 5087

## CLASSIFICATION

ISO 18273	S Al 5087 (AlMg4,5MnZr)	A-Nr	-
		F-Nr	22
		Mat-Nr	3.3546

## GENERAL DESCRIPTION

Designed to meet the tensile strength requirements of high magnesium alloys  
 For base metals with a max. of 5% Mg  
 The presence of Zirconium produces a fine-grained weld metal structure  
 Reduced tendency of solidification cracking in highly restrained welds

## SHIELDING GASES (ACC. ISO 14175)

I1	: Inert gas Ar (100%)
I3	: Inert gas Ar+ 0.5-95% He
Flow Rate	: 8 - 15 L/min

## APPROVALS

GL	LR	DB	TÜV	WIWeb
+	+	+	+	+

*\*(Valid for I1 and I3 gases)*

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Zr	Be
bal.	max. 0.25	max. 0.4	max. 0.05	0.7-1.1	4.5-5.2	0.05-0.25	max. 0.25	max. 0.15	0.10-0.20	max. 0.0003

Notes : Unspecified elements should not exceed a total of 0.15%

## MECHANICAL PROPERTIES. TYPICAL. ALL WELD METAL

	Shielding gas	Condition	Yield strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]
Typical values	I1	AW	125-140	275-300	17-30

## PHYSICAL PROPERTIES

Melting range	: 568 - 638°C
Density	: approximately 2660 kg/m3

## APPLICATIONS

Marine fabrication and repair	Railway Industry
Cryogenic tanks	Automotive Industry
Shipbuilding and other high strength structural aluminium applications	Trailer Industry and Offshore

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	4.0	4.8
5 kg cardboard box	X	X	X	X	X	X

SuperGlaze® TIG 5087: rev. C-EN02-01/02/15

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.



# SuperGlaze® TIG 5183

## CLASSIFICATION

<b>AWS 5.10</b>	R5183	<b>A-Nr</b>	-
<b>ISO 18273</b>	S Al 5183 [AlMg4.5Mn0.7(A)]	<b>F-Nr</b>	22
<b>EN 573.3</b>	EN AW-AlMg4.5Mn	<b>Mat-Nr</b>	3.3548

## GENERAL DESCRIPTION

Designed to meet the tensile strength requirements of magnesium alloys  
For base materials 5083 and 5654

## SHIELDING GASES (ACC. ISO 14175)

I1	: Inert gas Ar (100%)
I3	: Inert gas Ar+ 0.5-95% He
Flow Rate	: 8 - 15 L/min

## APPROVALS

ABS	GL	LR	DB	TÜV	DNV	BV	WlWeb
+	+	+	+	+	+	+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Be
bal.	max. 0.4	max. 0.4	max. 0.1	0.5-1.0	4.3-5.2	0.05-0.25	max. 0.25	max. 0.15	max. 0.0003

Notes : Unspecified elements should not exceed a total of 0.15%

## MECHANICAL PROPERTIES. TYPICAL. ALL WELD METAL

	Shielding gas	Condition	Yield strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]
<b>Typical values</b>	I1	AW	125-165	270-290	16-25

## PHYSICAL PROPERTIES

Melting range	: 568 - 638°C
Density	: approximately 2660 kg/m3

## APPLICATIONS

Marine fabrication and repair	Military Industry
Cryogenic tanks	Railway & Automotive Industry
Shipbuilding and other high strength structural aluminium applications	Trailer Industry and Offshore

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	4.0
<b>5 kg cardboard box</b>	X	X	X	X	X

SuperGlaze® TIG 5183: rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# SuperGlaze® TIG 5356

## CLASSIFICATION

<b>AWS 5.10</b>	R5356	<b>A-Nr</b>	-
<b>ISO 18273</b>	S Al 5356 (AlMg5Cr(A))	<b>F-Nr</b>	22
<b>EN 573.3</b>	EN AW-AlMg5	<b>Mat-Nr</b>	3.3556

## GENERAL DESCRIPTION

General purpose filler alloy for welding 5XXX series alloys when 276 MPa tensile strength is not required.  
Excellent colour match after anodizing

## SHIELDING GASES (ACC. ISO 14175)

I1	: Inert gas Ar (100%)
I3	: Inert gas Ar+ 0.5-95% He
Flow Rate	: 8 - 15 L/min

## APPROVALS

ABS	GL	LR	DB	TÜV	DNV	BV
+	+	+	+	+	+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Be
bal.	max. 0.25	max. 0.4	max. 0.1	0.05-0.2	4.5-5.5	0.05-0.20	max. 0.1	0.06-0.2	max. 0.0003

Notes : Unspecified elements should not exceed a total of 0.15%

## MECHANICAL PROPERTIES. TYPICAL. ALL WELD METAL

	Shielding gas	Condition	Yield strength [N/mm <sup>2</sup> ]	Tensile strength [N/mm <sup>2</sup> ]	Elongation [%]
<b>Typical values</b>	I1	AW	110-120	240-296	17-26

## PHYSICAL PROPERTIES

Melting range	: 562 - 633°C
Density	: approximately 2640 kg/m3

## APPLICATIONS

Structural frames in the shipbuilding industry  
Furniture, Storage tanks  
Railway Industry

Automotive and trailer Industry  
Formed truck panels  
Automotive bumpers and supports

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	4.0	5.0	
<b>5 kg cardboard box</b>	X	X	X	X	X	X	<i>Note : Cut length = 1000 mm</i>

SuperGlaze® TIG 5356 rev. C-EN22-01/02/16

# SuperGlaze® TIG 5554

## CLASSIFICATION

<b>AWS 5.10</b>	R5554	<b>A-Nr</b>	-
<b>ISO 18273</b>	Al 5554	<b>F-Nr</b>	
		<b>Mat-Nr</b>	

## GENERAL DESCRIPTION

## SHIELDING GASES (ACC. ISO 14175)

I1	: Inert gas Ar (100%)
I3	: Inert gas Ar+ 0.5-95% He
Flow Rate	: 8 - 15 L/min

## APPROVALS

ABS

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Be
bal.	max. 0.25	max. 0.4	max. 0.1	0.5-1.0	4.7-5.5	0.05-0.20	max. 0.25	0.05-0.20	max. 0.0003

Notes : *Unspecified elements should not exceed a total of 0.15%*

## MECHANICAL PROPERTIES. TYPICAL. ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation [%]
<b>Typical values</b>	I1	AW	125-145	275-295	17-25

## PHYSICAL PROPERTIES

Melting range	: 562 - 633°C
Density	: approximately 2660 kg/m3

## APPLICATIONS

Structural frames in the shipbuilding industry  
Furnitures. Storage tanks  
Railway Industry

Automotive and trailer Industry  
Formed truck panels  
Automotive bumpers and supports

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4
5 kg cardboard box	X	X	X

Superglaze® TIG 5554 rev. C-EN01-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

**LINCOLN**  
**ELECTRIC**  
THE WELDING EXPERTS®

# SuperGlaze® TIG 5754

## CLASSIFICATION

<b>AWS 5.10</b>	Al 5754	<b>A-Nr</b>	-
<b>ISO 18273</b>	S Al 5754 (AlMg3)	<b>F-Nr</b>	22
		<b>Mat-Nr</b>	3.3536

## GENERAL DESCRIPTION

Magnesium alloyed aluminium for welding of alloys with a maximum of 3.5% Mg  
 Good corrosion resistance and excellent colour match after anodizing  
 Suitable for a wide range of applications in general construction and structural industry

## SHIELDING GASES (ACC. ISO 14175)

I1	: Inert gas Ar (100%)
I3	: Inert gas Ar+ 0.5-95% He
Flow Rate	: 8 - 15 L/min

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Be
bal.	max. 0.4	max. 0.4	max. 0.1	max. 0.5	2.6-3.6	max. 0.3	max. 0.20	max. 0.15	max. 0.0003

Notes : Unspecified elements should not exceed a total of 0.15%

## MECHANICAL PROPERTIES. TYPICAL. ALL WELD METAL

	Shielding gas	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)
<b>Typical values</b>	I1	AW	70-80	180-200	15-20

## PHYSICAL PROPERTIES

Melting range	: 580 - 642°C
Density	: approximately 2660 kg/m3

## APPLICATIONS

General Construction Industry  
 Automotive bumpers and supports

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.4	3.2	4.0	Note : Cut length = 1000 mm
<b>5 kg cardboard box</b>	X	X	X	X	X	

Superglaze® TIG 5754: rev. C-EN01-01/02/16

# LNG I

## CLASSIFICATION

<b>AWS 5.2</b>	R45*	<b>A-Nr</b>	1	<b>Mat-Nr</b>	1.0324
<b>EN 12536</b>	01	<b>F-Nr</b>	6		
* Nearest classification		<b>Mat-Nr</b>	-		

## GENERAL DESCRIPTION

Rods for oxy-acetylene gas welding of general construction steel  
 Suitable for mild steel  
 Max. design temperature 350°C

## CHEMICAL COMPOSITION (W%) TYPICAL WIRES

C	Mn	Si	P	S	Cr	Ni	Mo
0.07	0.5	0.1	0.01	0.01	0.04	0.03	0.01

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) +20°C
Typical values	AW	280	390	16	50

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Type
Pipe material	L210 up to L290
General structural steels	S185 up to S275

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	3.0
5 kg cardboard box	X	X

LNG I rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.



# LNG II

## CLASSIFICATION

<b>AWS 5.2</b>	R60*	<b>A-Nr</b>	1	<b>Mat-Nr</b>	1.0349
<b>EN 12536</b>	O II	<b>F-Nr</b>	6		
	* Nearest classification	<b>Mat-Nr</b>	-		

## GENERAL DESCRIPTION

Rods for oxy-acetylene gas welding of general construction steel  
 Suitable for mild steel  
 max. design temperature 350°C  
 Higher strength than LNG I

## CHEMICAL COMPOSITION (W%) TYPICAL WIRES

C	Mn	Si	P	S
0.10	1.1	0.15	0.01	0.01

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition	Yield strength (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )	Elongation (%)	Impact ISO-V(J) +20°C
Typical values	AW	320	430	17	60

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Type
Pipe material	L210 up to L290
General structural steels	Si85 up to S275

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	1.6	2.0	2.5	3.0	4.0
5 kg cardboard box	X	X	X	X	X

LNG II: rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.

# LNG IV

## CLASSIFICATION

<b>AWS 5.2</b>	R65*	<b>A-Nr</b>	2	<b>Mat-Nr</b>	1.5425
<b>EN 12536</b>	O IV	<b>F-Nr</b>	6		
	* Nearest classification	<b>Mat-Nr</b>	-		

## GENERAL DESCRIPTION

Rods with 0.5% Mo for oxy-acetylene gas welding of fine grained and creep resisting steel  
Design temperature max. 500°C

## APPROVALS

TÜV

+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRES

C	Mn	Si	P	S	Mo
0.09	1.0	0.19	0.01	0.01	0.50

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition	Yield strength	Tensile strength	Elongation	Impact ISO-V(J)
		(N/mm <sup>2</sup> )	(N/mm <sup>2</sup> )	(%)	+20°C
Typical values	AW	380	500	22	60

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
Pipe material	EN 10208-2	L210 up to L290
General structural steels		S185 up to S275
Boiler and pressure vessel steel		P295, P355, 16Mo3

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.0	2.5	3.0	4.0
5 kg cardboard box	X	X	X	X

LNG IV: rev. C-EN23-01/02/16

All information in this data sheet is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information. Fumes: Safety Data Sheets (SDS) are available on our website.



GTAW